

## Fire Cement Tr UK

Revision: 6/12/2021

Page 1 from 1

### Technical data

Basis	Sodium silicate
Consistency	Stable paste
Curing system	Physical drying
Density	1,82 g/ml
Maximum allowed distortion (ISO 11600)	Ca. 2 %
Temperature resistance**	-40 °C → 1500 °C
Application temperature	5 °C → 30 °C

\* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. \*\* This information relates to fully cured product.

### Product description

Fire Cement Tr UK is a high quality sealing paste based on sodium silicate.

### Joint dimensions

*Min. width for joints:* 5 mm

*Max. width for joints:* 15 mm

### Properties

- Ready for use
- Not elastic after curing
- No fragmentation or cracking after curing
- Heat resistant up to 1500°C
- Free of asbestos

### Application method

*Application method:* Apply with spatula, filling knife or sealing gun.

*Cleaning:* Before curing, Fire Cement Tr UK can be removed with water from substrates and tools.

*Finishing:* Finish with a spatula or putty knife.

*Repair:* With the same material.

### Applications

- Sealing of joints and openings where high temperatures are possible.
- Sealing of stoves, ovens, fireplaces.

### Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult label and material safety data sheet for more information.

Dangerous. Respect the precautions for use.

### Packaging

*Colour:* anthracite

*Packaging:* 290 ml cartridge

### Remarks

- A slight warming of the heating installation during 12 hours after application prevents bubbleforming and improves structure.
- With prolonged exposure to very high temperatures, the color may lighten.

### Shelf life

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C. Protect against frost.

### Liability

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

### Substrates

*Substrates:* brick, concrete, metals

*Nature:* rigid, clean, dry, free of dust and grease.

*Surface preparation:* Slightly moistening porous surfaces improves the adhesion.

We recommend a preliminary adhesion test on any substrate.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.